

Model: Fremont-R Natural  
 Size: 19'2X119'3 cm (7.6x47.0 in)  
 Thickness: 11mm  
 Material type: Porcelain



## TECHNICAL DATA

Manufacture process	Single-firing	Dry pressed ceramic tile
Length, width, thickness, side straightness, orthogonality, flatness	Conforms to the requisites applicable to each model as defined in standard UNE-EN 14411 for Group BIa annex G	
Water absorption	E < 0.5%	UNE EN ISO 10545 Part 3
Flexion resistance (N/mm.2) and breaking strength (N)	> 35 > 1300	UNE EN ISO 10545 Part 4
Resistance to surface abrasion (Glazed tiles)	4	UNE EN ISO 10545 Part 7
Lineal thermic dilatation	< 9*10 <sup>-6</sup> /°C	UNE EN ISO 10545 Part 8
Thermic impact resistance	Stands the test	UNE EN ISO 10545 Part 9
Cracking resistance	Stands the test	UNE EN ISO 10545 Part 11
Frost resistance	Stands the test	UNE EN ISO 10545 Part 12
Slip resistance	Class 1	UNE ENV 12633:2003
	R10	DIN 51130
	Class A	DIN 51097

## CHEMICAL RESISTANCE

Domestic cleaning products	Class GA	
Swimming pool salt	Class GA	UNE EN ISO 10545 Part 13
Acids and bases (low concentration)	Minimum Class GLB	
Stains resistance	Minimum Class 4	UNE EN ISO 10545 Part 14


## CE MARKING



CE Declaration of performance:

Nº 001VV2013

## IMPORTANT



< 25%

Interlocked laying maximum 25%