

Model: Adamant Okinawa Carbon

Size: 22X38 cm (8.7x15.0 in)

Thickness:

Material type: Porcelain



TECHNICAL DATA

Manufacture process	Single-firing	Dry pressed ceramic tile
Length, width, thickness, side straightness, orthogonality, flatness	Conforms to the requisites applicable to each model as defined in standard UNE-EN 14411 for Group BIa annex G	UNE EN ISO 10545 Part 2
Water absorption	$E < 0.5\%$	UNE EN ISO 10545 Part 3
Flexion resistance (N/mm.2) and breaking strength (N)	> 35 > 1300	UNE EN ISO 10545 Part 4
Lineal thermic dilatation	$< 9 \cdot 10^{-6} / ^\circ\text{C}$	UNE EN ISO 10545 Part 8
Thermic impact resistance	Stands the test	UNE EN ISO 10545 Part 9
Cracking resistance	Stands the test	UNE EN ISO 10545 Part 11
Frost resistance	Stands the test	UNE EN ISO 10545 Part 12

CHEMICAL RESISTANCE

Domestic cleaning products	Class GA	
Swimming pool salt	Class GA	UNE EN ISO 10545 Part 13
Acids and bases (low concentration)	Minimum Class GLB	
Stains resistance	Minimum Class 4	UNE EN ISO 10545 Part 14

CE MARKING



CE Declaration of performance:

Nº 001VV2013